


# TECHNICAL DATA SHEET

Dy-Mark (Aust) Pty Ltd  
PO Box 1556 Toowong 4066  
Phone: 1300 396 275 Fax: 1300 360 440  
[www.dy-mark.com.au](http://www.dy-mark.com.au)



## Dy-Mark® METALPRO ZINC GAL® (BULK)



Dy-Mark® MetalPro Zinc Gal® is a zinc rich, high performance heavy duty corrosion inhibitive primer suitable for use on ferrous metals such as steel, iron and galvanised iron. Zinc Gal contains 99% pure zinc and 91% metallic zinc pigment in the dry film. It is used extensively in metal fabrication and gives superior cathodic protection to weld joints. Suitable for use on fences & gates, balustrades, rails, ducting and trailers. Zinc Gal® conforms to AS3750.9:2009 Type 1. It dries to a matt grey finish.

### DIRECTIONS FOR USE

#### Suitable Surfaces:

Steel, wrought iron and galvanised iron.

#### Ideal Application Temperature:

Between 10°C and 35°C.

#### Preparation:

Surface should be clean, dry and free from contaminants such as rust, oil, grease, dirt and salt. Surface should be thoroughly ground back to clean white metal. For best results abrasive blast clean to AS1627.4 Class 2. Remove all traces of rust and any old paint with a wire brush, scraper or mechanical sander. Zinc Gal® should not be painted over rusty steel. Correct surface preparation is essential for obtaining maximum coating performance.

#### Application:

The product can be applied with brush, roller or spray (airless or conventional). Stir the can thoroughly until the product is uniform with a flat stirrer. Continue mixing frequently during use.

#### Brush/Roller:

Apply even coats of the mixed material to the prepared surface. Thin if necessary for ease of application (maximum of 5% Xylene Thinner). When brushing/rolling additional coats may be required to achieve desired thickness.

#### Conventional Spraying:

Agitate paint pot regularly to avoid settling of the product. If necessary, thin the product with a maximum of 15-20% Xylene Thinner and apply at the pressure of 40-60psi.

#### Coverage:

Approximately 6m<sup>2</sup> per litre at 75 micron recommended dry film thickness.

#### Drying Time:

Touch dry in 30-45 minutes (25°C).

Recoat after 4 hours.

Dry to handle (Hard dry) in 16-24 hours.

Drying will be slower in cold and humid conditions, in the absence of ventilation or where heavy film build is applied.

#### Clean Up:

Clean brushes, equipment and wet paint with Mineral Turps or Xylene Thinner.

# TECHNICAL DATA SHEET

Dy-Mark (Aust) Pty Ltd  
PO Box 1556 Toowong 4066  
Phone: 1300 396 275 Fax: 1300 360 440  
[www.dymark.com.au](http://www.dymark.com.au)



## TECHNICAL DATA

|                        |                                  |
|------------------------|----------------------------------|
| <b>Size:</b>           | 250ml, 500ml, 1L                 |
| <b>Colour:</b>         | Grey                             |
| <b>Finish:</b>         | Matt                             |
| <b>Consistency:</b>    | Liquid                           |
| <b>Resin Type:</b>     | Epoxy – one pack                 |
| <b>VOC:</b>            | <535g/L                          |
| <b>Specifications:</b> | Conforms to AS3750.9:2009 Type 1 |

**Note:** Zinc Gal<sup>®</sup> is designed to be sprayed onto clean bare metal **after** it has been welded. It is not recommended for use as a weld through primer.

## STORAGE

Store locked up. Store in a well-ventilated place. Keep cool. Keep container tightly closed.

**CAUTION:** May develop pressure in storage. Open carefully wearing gloves and eye protection. Lever lid off gradually. Don't allow water to contaminate paint as this may result in build up of pressure.

## DISPOSAL

Dispose of contents/container according to regional regulations. Do not pour unwanted paint down the drain. Keep unwanted paint in sealed containers for disposal via chemical waste collections. Empty paint containers should be left open in a well-ventilated area to dry out. When dry, empty containers are recyclable via steel can recycling programs.

## FIRST AID / SAFETY INFORMATION

Please refer to Safety Data Sheet before use. Safety data sheets are available from our website [www.dymark.com.au](http://www.dymark.com.au) or from the following QR code:



**Contact a POISONS INFORMATION CENTRE:** Australia 13 11 26, New Zealand 0800 764 766 or doctor/physician if you feel unwell.

**KEEP OUT OF REACH OF CHILDREN.**

# TECHNICAL DATA SHEET

**Dy-Mark (Aust) Pty Ltd**  
PO Box 1556 Toowong 4066  
Phone: 1300 396 275 Fax: 1300 360 440  
[www.dymark.com.au](http://www.dymark.com.au)



## DISCLAIMER

The information provided within this Technical Data Sheet is intended as a guide only. The performance of this product will depend on many factors outside the control of Dy-Mark®; including surface preparation, surface-specific conditions, surface types, correct application and environmental conditions.

Dy-Mark® recommends customers undertake their own risk assessment prior to use, to determine the suitability of the product for the particular use intended.

It is essential that a sample of the product be applied to the intended area of use to ensure it is acceptable in appearance and finish and that it performs on the specific surface.

For further information please contact the Dy-Mark® Sales and Customer Support Centre on 1300 396 275.